

PRODUCT INFORMATION

STEEL GRIT ANGULAR

Applications: Cleaning, roughening

Preparation of surfaces for plastic or rubber-metal combinations,
blasting work where specific roughness levels have to be achieved

Use: Centrifugal wheel an compressed air systems



SIEVING RANGES

	mm
G-14	1,18 - 2,00
G-16	1,00 - 1,70
G-18	0,71 - 1,40
G-25	0,42 - 1,18
G-40	0,30 - 1,00
G-50	0,18 - 0,71
G-80	0,12 - 0,42

CHEMICAL COMPOSITION

C	0,80 - 1,20%
Si	≤ 0,40%
Mn	0,60 - 1,20%
S	≤ 0,05%
P	≤ 0,05%

TECHNICAL DATA

Specific gravity	ca. 7,40 kg / l
Bulk density	ca.3,7 kg / l
	HV 1,0 ca. 510 - 590
	HRC 50 - 55