

## PRODUCT INFORMATION

# STAINLESS STEEL-SHOT CR/NI STAINLESS STEEL-GRIT CR

**Applications:** Cleaning, shot peening of stainless steel and non-ferrous metals .  
Cr/Ni is rust resistant. Cr is harder and is therefore more suited to mechanical applications.

**Use:** Centrifugal wheel and compressed air systems.



## SIEVING RANGES

No.	mm
10	0,05 - 0,20
20	0,10 - 0,30
30	0,15 - 0,40
40	0,30 - 0,60
60	0,50 - 1,20
100	0,80 - 1,70
150	1,20 - 2,30
200	1,70 - 3,30

## CHEMICAL COMPOSITION

Cr/Ni		Cr	
Cr	16 - 18 %	Cr	14 - 16%
Ni	8 - 9%	Ni	0 - 2%
Cmax	0,25%	C	0,4%
Si	2,0%	Si	2,0%

## TECHNICAL DATA

Hardness :	300 HV
Shape:	round